

Data sheet

Filter paper

Parameter*	Value*
Grade	MN 85/70
Basis weight	73 g/m ²
Thickness	0.42 mm / 16.5 mil
Filtration speed	15 s
Maximum temperature	200 °C / 392 °F
Surface	Smooth
Color	White
Material	Borosilicate glass micro fibers
Average retention capacity	0.6 µm
Characteristics / Application	Glass fiber filter with organic binder

*These data are typical values and must not be regarded as specification.



Management
System
EN ISO 13485:2016
ISO 9001:2015

www.tuv.com
ID 0000056401



18.02.2026 · Rev. 1 · www.mn-net.com

MACHEREY-NAGEL GmbH & Co. KG · Valencienner Str. 11 · 52355 Düren · Germany

DE +49 24 21 969-0 info@mn-net.com
CH +41 62 388 55 00 sales-ch@mn-net.com

FR +33 388 68 22 68 sales-fr@mn-net.com
US +1 888 321 62 24 sales-us@mn-net.com