

# TECHNICAL DATA SHEET

## SELF SEAL POUCH (60 gr)

<b>PRODUCT CODE</b>	:	<b>KP</b>
<b>RELATED STANDARDS</b>	:	PMSSteripack flat and gusseted reels are manufactured according to EN 868-5 and ISO 11607 standards. The indicator used in the pouch production is classified as Class 1 Type Indicator according to the ISO 11140-1 standard. PMS Steripack self seal pouches meet the requirements of 93/42/EEC Medical Device Directive regulations
<b>INTENDED USE</b>	:	PMSSteripack self seal pouches are used for the packing of the Medical Devices before sterilization and it maintains the sterility of the products after sterilization. PMSSteripack self seal pouches are ease to package and indicator used for the sterilization provides information with the sterilization status of the medical devices.
<b>OPERATION CONDITIONS</b>	:	PMSSteripack reels are used for steam, ethylene oxide, formaldehyde sterilization methods. The sterilization conditons should be determined by the end user regarding to material to be sterilized.

### SPECIFICATIONS :

	PROPERTIES	UNIT	STANDARD	TYPICAL VALUE	
<b>MEDICAL PAPER</b>	SUBSTANCE	g/m <sup>2</sup>	ISO 536	60	
	THICKNESS	µm	ISO 534	83	
	BENDTSEN POROSITY	ml/mn	ISO 5636-3	1000	
	AIR PERMEANCE	µm/(Pa.s)	ISO 5636-3	11,4	
	BENDTSEN ROUGHNESS FS	ml/mn	ISO 8791-2	375	
	BENDTSEN ROUGHNESS WS	ml/mn	ISO 8791-2	375	
	TENSILE STRENGTH /MD	kN/m	EN ISO 1924-2	6,4	
	TENSILE STRENGTH /CD	kN/m	EN ISO 1924-2	3,4	
	WET TENSILE STRENGTH /MD	kN/m	ISO 3781	2,1	
	WET TENSILE STRENGTH /CD	kN/m	ISO 3781	1,1	
	BURST STRENGTH	kPa	ISO 2758	350	
	TEARING STRENGTH /MD	mN	ISO 1974	600	
	TEARING STRENGTH /CD	mN	ISO 1974	650	
	WET BURST	kPa	ISO 3689	150	
	WATER REPELLENCY	s	EN 868-2 (app.D)	35	
	PORE SIZE	µm	EN 868-2 (app.E)	21	
	COBB TEST (60 s)	g/m <sup>2</sup>	ISO 535	15	
	FLUORESCENCE	pts/dm <sup>2</sup>	EN 868-2 (app.B)	0	
	pH: between 5.0 and 8.0 (ISO6588-2)		Chloride content < 0,05% ( ISO 9197 )		
			Sulphate Content < 0,25% (ISO9198)		
FREE FROM LEAD AND HEAVY METALS AND TOXIC MATERIALS					



**PMS Steripack®**

## SELF SEAL POUCH (60 gr)

LAMINATED FILM	PROPERTIES	UNIT	STANDARD	TYPICAL VALUE		
	THICKNESS	Micron	ASTM D 374	LAM.FILM	53 ± 5	
				PP	40 ± 5	
				PET	12 ± 2	
	COF	F/M	ASTM F 1894	0,30-0,35		
		M/M		0,35-0,40		
	THERMAL SEAL	°C	ASTM F 88	150 ± 5		
	TEAR	G	MD TD	D1922	40 ± 5	
50 ± 5						
GLOSS	%	ASTMD 2457	150 ± 5			
FREE FROM LEAD AND HEAVY METALS AND TOXIC MATERIALS						

### PRODUCT SPECIFICATIONS

POUCH	PROPERTIES	UNIT	STANDARD	TYPICAL VALUE		
	SEAL STRENGTH	cm	ASTM F 88	< 25	≥ 25	
		Edge Seal (gr /15 mm) (N)		3,0 ± 0,5	4,0 ± 0,75	
		Top Seal (gr /15 mm) (N)		4,0 ± 0,5	5,0 ± 0,5	
	BUBBLE TEST		ASTM F2096-04	None		
	PINHOLE DETERMINATION		EN 868-5 Annex C	None		
	DIMENSION CONTROL	cm or mm	ASTM F2203-02	Desired dimensions		
	LEAKAGE TEST		ASTM F1929-98	None		
PEEL DIRECTION		EN 868-5 Annex E	Must not break the particle			
INDICATOR CONTROL		ISO 11140-1	Must return the specified color			

INDICATOR	STERILIZATION METHOD	BEFORE STERILIZATION	AFTER STERILIZATION
	STEAM	Pink	Brown / Black
	EO	Green	Yellow / Orange
	FORMALDEHYDE	Red	Green

### PACKAGING

: PMS Self Seal Pouches are packaged as 200 pieces in a box.



**PMS Steripack®**